

# LOCTITE STYCAST E 2534 FR CAT 24LV

January 2017

## PRODUCT DESCRIPTION

LOCTITE STYCAST E 2534 FR CAT 24LV provides the following product characteristics:

<b>Technology</b>	Epoxy
Appearance (Resin)	Blue
Components	Two components - requires mixing
Mix Ratio, (by weight) Resin : Hardener	100 : 8
Product Benefits	<ul style="list-style-type: none"> <li>Flame retardant</li> <li>Halogen free</li> <li>High thermal conductivity</li> <li>High dielectric strength</li> </ul>
<b>Cure</b>	Heat cure
<b>Application</b>	Potting
Operating Temperature - Continuous	-65 to +105°C
Operating Temperature - Intermittent	-65 to +120°C
UL Flammability Rating	UL 94 V-0 @ 6 mm thickness

LOCTITE STYCAST E 2534 FR CAT 24LV epoxy potting compound complies with recent demands on environmentally friendly products and does not contain brominated flame retardants.

LOCTITE STYCAST E 2534 FR can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

## TYPICAL UNCURED PROPERTIES AS MIXED

### LOCTITE STYCAST E 2534 FR CAT 24LV with LOCTITE CAT 24LV

Viscosity, Brookfield - DV-2+, 25 °C, mPa·s (cP):  
 Spindle 6, speed 20 rpm 3,290  
 Flash Point - See SDS

## TYPICAL CURING PERFORMANCE

### Cure Schedule

4 hours @ 65°C (Convection Box Oven)

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Hardness, Shore D	91
Thermal Conductivity, W/(m·K)	0.99
Young's Modulus:	
@ -40°C	N/mm <sup>2</sup> 5,224 (psi) (757,677)
@ 0°C	N/mm <sup>2</sup> 4,479 (psi) (64,962)
@ 25°C	N/mm <sup>2</sup> 4,285 (psi) (621,486)
@ 50°C	N/mm <sup>2</sup> 4,073 (psi) (590,738)
@ 100°C	N/mm <sup>2</sup> 122 (psi) (17,694)
@ 150°C	N/mm <sup>2</sup> 120 (psi) (17,404)

### Glass Transition Temperature, °C:

DMA, Tangent Delta	89
TMA	60

### Coefficient of Thermal Expansion, TMA:

Below Tg, $\mu\text{m}/\text{m}^\circ\text{C}$	39
Above Tg, $\mu\text{m}/\text{m}^\circ\text{C}$	147

### Electrical Properties

Volume Resistivity, ohms-cm	$1.2 \times 10^{15}$
Surface Resistivity, ohms	$4.6 \times 10^{14}$
Dielectric Constant / Dissipation Factor :	
50Hz	4.9 / 0.023
1 kHz	5.0 / 0.014
1 MHz	4.6 / 0.022

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Tensile Lap Shear Strength :

Al to Al	N/mm <sup>2</sup> 16 (psi) (2,320)
----------	---------------------------------------

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

## DIRECTIONS FOR USE

- Some filler settling is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use. Power mixing is preferred to ensure a homogeneous product.
- Moderate warming to maximum 40°C of the resin prior to adding the hardener will improve pourability.
- Pour mixture into cavity or mold.
- IMPORTANT:** DO NOT USE CATALYST 27-1 as this hardener is

not compatible with the filler, and will cause foaming.

#### STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

#### Optimal Storage : 18 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\text{N} \times 0.225 = \text{lb/F}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{psi} \times 145 = \text{N/mm}^2$

$\text{MPa} = \text{N/mm}^2$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{cP}$

#### Disclaimer

##### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to

determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage:** [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference 2

Americas  
+1.888.943.6535

Europe  
+32.1457.5611

Asia  
+86.21.2891.8000

**For the most direct access to local sales and technical support visit: [www.henkel.com/electronics](http://www.henkel.com/electronics)**